

DANAMID FGF- 20

PA6-GF20

Qualchem Zrt.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	5700	MPa	ISO 527
Stress at break	110	MPa	ISO 527
Strain at break	4	%	ISO 527

Electrical properties	Value	Unit	Test Standard
ISO Data			
Comparative tracking index	550	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1260	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Europe