

N6G20

PA6-GF20

Cheng Yu Plastic Company Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.012	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	170	MPa	ASTM D 638
Flexural Strength	260	MPa	ASTM D 790
Rockwell Hardness	M 94	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dielectric Constant, 60 Hz	3.5	-	ASTM D 150
Surface Resistivity	1E14	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1270	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

Asia Pacific