

Product Texts

Polyamide 66, 20% glass fiber reinforced, heat-aging stabilized, for injection moulding

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
^[C] Molding shrinkage, parallel	0.6 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.1 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	5800 / -	MPa	ISO 527
^[C] Stress at break	125 / -	MPa	ISO 527
^[C] Strain at break	3 / -	%	ISO 527
^[C] Charpy impact strength, +23°C	50 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	10 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 0.45 MPa	245 / *	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	250 / *	°C	ISO 306
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1430 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Special Characteristics

Heat stabilized or stable to heat

Features

Tribologic Grade