

LUVOCOM 19-7744 VP

(PA46+PTFE)-AF

LEHVOSS Group

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2900	MPa	ISO 527
Tensile Strength	65	MPa	ISO 527
Flexural modulus, 23°C	2600	MPa	ISO 178
Charpy impact strength, +23°C	32	kJ/m ²	ISO 179/1eU

Other properties	Value	Unit	Test Standard
Density	1400	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 8	h	-
Processing humidity	≤0.1	%	-
Melt temperature	310	°C	-
Mold temperature	90 - 130	°C	-
Zone 1	285 - 315	°C	-
Zone 2	305 - 315	°C	-
Zone 3	305 - 315	°C	-
Nozzle temperature	280 - 330	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Features

Tribologic Grade

Applications

Automotive, IT / Business Machine

Regional Availability

North America, Europe, Asia Pacific