

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.1	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.6	%	ISO 294-4, 2577

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	185	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	210	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1270	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form

Black