

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>8400 / 5000</b>	MPa	ISO 527
Tensile Strength	<b>148 / 91</b>	MPa	ISO 527
Strain at break	<b>3 / 5</b>	%	ISO 527
Charpy impact strength, +23°C	<b>43 / 51</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>6.5 / 9</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>200 / *</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>215 / *</b>	°C	ISO 75-1/-2
Burning behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
<b>Electrical properties</b>			
<b>ISO Data</b>			
Surface resistivity	<b>* / 1E12</b>	Ohm	IEC 62631-3-2
Electric strength	<b>40 / 35</b>	kV/mm	IEC 60243-1
<b>Other properties</b>			
Density	<b>1300 / -</b>	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets, Natural Color

### Additives

Lubricants

### Special Characteristics

Heat stabilized or stable to heat

### Regional Availability

Europe