

PlusTek PB825G5BK10

PA6-GF25

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	7250	MPa	ISO 527
Tensile Strength	125	MPa	ISO 527
Strain at break	3.5	%	ISO 527
Izod notched impact strength, +23°C	21.5	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Other properties			
Humidity absorption	2	%	Sim. to ISO 62
Density	1280	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.15	%	-
Mold temperature	55 - 90	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	230 - 240	°C	-
Zone 2	230 - 240	°C	-
Zone 3	230 - 270	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Black

Special Characteristics

High impact or impact modified

Certifications

RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa