

SLOVAMID®6 GF 25 E LS

PA6-GF25

Plastcom, spol. s r.o.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6	g/10min	ISO 1133
Temperature	275	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	8500	MPa	ISO 527
Tensile Strength	115	MPa	ISO 527
Flexural modulus, 23°C	5300	MPa	ISO 178
Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	222	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	250	°C	ISO 75-1/-2
Vicat softening temperature, B	250	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Electrical properties			
ISO Data			
Electric strength	25	kV/mm	IEC 60243-1
Other properties			
Density	1270	kg/m ³	ISO 1183
Moisture Content	0.15	%	-

Characteristics**Processing**

Other Extrusion

Special Characteristics

U.V. stabilized or stable to weather

Delivery form

Natural Color

Regional Availability

Europe