

**Taromid B 280 G5 Y0**

PA6-GF25

Taro Plast S.p.A.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>8400</b>	MPa	ISO 527
Stress at break	<b>125</b>	MPa	ISO 527
Strain at break	<b>2.6</b>	%	ISO 527
Flexural modulus, 23°C	<b>8000</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>34</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>7.4</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>ASTM Data</b>			
Izod Impact notched, 1/8 in	<b>80</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>222</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>205</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>210</b>	°C	ISO 306
Burning behav. at 1,5 mm nom. thickn.	<b>V-0</b>	class	IEC 60695-11-10
Burning behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>3.2</b>	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>0.75</b>	mm	-
Limiting Oxygen Index	<b>30</b>	%	ASTM D 2863

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Comparative tracking index	<b>600</b>	-	IEC 60112

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water absorption	<b>7</b>	%	Sim. to ISO 62
Density	<b>1380</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Additives**

Release agent

**Features**

Low Odor

**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

**Regional Availability**

Europe