

Product Texts

Vydyne PF005 is a 25% glass fiber reinforced PA6 for injection molded applications.

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Stress at break	145 / -	MPa	ISO 527
^[C] Strain at break	3 / -	%	ISO 527

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1310 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe

Delivery form

Pellets