

AKROMID® B3 GF 30 S1 LA black (7704)

PA6-GF30

Akro-Plastic GmbH

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	9000 / 5500	MPa	ISO 527
Stress at break	150 / 100	MPa	ISO 527
Strain at break	3.5 / 10	%	ISO 527
Charpy impact strength, +23°C	95 / 120	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	90 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	17 / -	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-

Other properties	dry / cond	Unit	Test Standard
Density	1330 / -	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	270	°C	-
Mold temperature	80	°C	-
Injection pressure	75	MPa	-

Characteristics**Processing**

Injection Molding

Features

Laser Markable

Delivery form

Black

Applications

Automotive, Electrical and Electronical

Special Characteristics

High impact or impact modified

Regional Availability

Europe, Asia Pacific