

DANAMID FGFL0 - 30

PA6-GF30

Qualchem Zrt.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	6400	MPa	ISO 527
Stress at break	100	MPa	ISO 527
Strain at break	3.5	%	ISO 527

Electrical properties	Value	Unit	Test Standard
ISO Data			
Comparative tracking index	450	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1500	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Flame retardant

Regional Availability

Europe