

**AKROMID® C3 1 FR grey (4298)**

(PA66+PA6)

Akro-Plastic GmbH

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	1.2 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.3 / *	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	3500 / 1300	MPa	ISO 527
Yield stress	75 / 45	MPa	ISO 527
Charpy impact strength, +23°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	90 / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	4 / -	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	3 / -	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	70 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	210 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Burning behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	-
Oxygen index	34 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	0.4	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	0.8	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (3)	1.6	mm	-
Glow Wire Ignition Temperature (GWIT)	750	°C	IEC 60695-2-13
GWIT - thickness tested (1)	0.4	mm	-
Glow Wire Ignition Temperature (GWIT)	750	°C	IEC 60695-2-13
GWIT - thickness tested (2)	0.8	mm	-
Glow Wire Ignition Temperature (GWIT)	750	°C	IEC 60695-2-13
GWIT - thickness tested (3)	1.6	mm	-

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Electric strength	10 / -	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	-	IEC 60112

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Density	1170 / -	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	300	°C	-
Mold temperature	90	°C	-
Injection pressure	75	MPa	-

**Characteristics****Processing**

Injection Molding

**Applications**

Electrical and Electronical

## AKROMID® C3 1 FR grey (4298)

(PA66+PA6)

Akro-Plastic GmbH

### Special Characteristics

Flame retardant, Halogen-free, Heat stabilized or stable to heat

### Regional Availability

Europe, Asia Pacific

### Certifications

RoHS compliant