

**Product Texts**

Injection Molding, 30% Glass Reinforced, Heat Stabilized

ISO 1043 PA6-GF30

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	9600 / 5900	MPa	ISO 527
<sup>[C]</sup> Stress at break	170 / 100	MPa	ISO 527
<sup>[C]</sup> Strain at break	3.5 / 6.5	%	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1000h	* / 4100	MPa	ISO 899-1
<sup>[C]</sup> Charpy impact strength, +23°C	80 / 95	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	70 / 70	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	15 / 20	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	10 / 10	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	200 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	215 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	80 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Water absorption	7 / *	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	2.1 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1360 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Viscosity number	140 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.12	%	-
Melt temperature	270 - 290	°C	-
Mold temperature	80 - 120	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Additives**

Release agent

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information****Injection molding**

## PREPROCESSING

Residual moisture content: 0.03 - 0.12%

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

## PROCESSING

Melt temperature (Tmin - Tmax): 270 - 290 °C

Mold temperature: 80 - 120 °C