

**AKROMID® C3 5 S3 black (4605)**

(PA66+PA6)

Akro-Plastic GmbH

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	1.4 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.6 / *	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	2500 / 900	MPa	ISO 527
Yield stress	65 / 45	MPa	ISO 527
Charpy impact strength, +23°C	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	7 / 23	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	5 / -	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	160 / *	°C	ISO 75-1/-2

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Density	1120 / -	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	300	°C	-
Mold temperature	90	°C	-
Injection pressure	75	MPa	-

**Characteristics****Processing**

Injection Molding

**Applications**

Automotive, Electrical and Electronical

**Delivery form**

Black

**Regional Availability**

Europe, Asia Pacific

**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat