

NG30-01NC

PA6-GF30

Next Polymers Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0085	mm/mm	ASTM D 955
Mechanical properties	dry / cond	Unit	Test Standard
ASTM Data			
Tensile Strength	170 / 110	MPa	ASTM D 638
Elongation at Break	4 / 7	%	ASTM D 638
Flexural Modulus	8600 / 6000	MPa	ASTM D 790
Flexural Strength	235 / 180	MPa	ASTM D 790
Rockwell Hardness	R 125 /	-	ASTM D 785
Izod Impact notched, 1/8 in	118 / 235	J/m	ASTM D 256
Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.8	mm	-
DTUL @ 66 psi	210	°C	ASTM D 648
DTUL @ 264 psi	200	°C	ASTM D 648
Melting Temperature	220	°C	ASTM D 3418
Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Volume resistivity	1E12 / -	Ohm*m	IEC 62631-3-1
Electric strength	30 / 25	kV/mm	IEC 60243-1
Comparative tracking index	500 / -	-	IEC 60112
Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	2.25	%	ASTM D 570
Water Absorption, Equilibrium	6.3	%	ASTM D 570
Density	1360	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Applications

Automotive, Electrical and Electronical, General Purpose

Delivery form

Natural Color

Regional Availability

Asia Pacific