

LUPOX TE5011M

(PBT+PC)

LG Chem

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0085	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	47.1	MPa	ASTM D 638
Elongation at Break	100	%	ASTM D 638
Flexural Modulus	1864	MPa	ASTM D 790
Flexural Strength	68.7	MPa	ASTM D 790
Izod Impact notched, 1/4 in	660	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	110	°C	ASTM D 648
DTUL @ 264 psi	91	°C	ASTM D 648
Melting Temperature	225	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4 - 5	h	-
Processing humidity	≤0.02	%	-
Melt temperature	260 - 270	°C	-
Mold temperature	60 - 80	°C	-
Zone 1	250 - 260	°C	-
Zone 2	250 - 260	°C	-
Zone 3	255 - 265	°C	-
Nozzle temperature	260 - 270	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America