

PlusTek PB335G7NT

PA6-GF30

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	11400	MPa	ISO 527
Tensile Strength	200	MPa	ISO 527
Strain at break	3.7	%	ISO 527
Flexural modulus, 23°C	9000	MPa	ISO 178
Flexural strength	310	MPa	ISO 178
Izod notched impact strength, +23°C	19	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	203	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
Other properties			
Water absorption	5.5	%	Sim. to ISO 62
Humidity absorption	1.7	%	Sim. to ISO 62
Density	1410	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Mold temperature	65 - 80	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	240 - 280	°C	-
Zone 2	240 - 280	°C	-
Zone 3	240 - 280	°C	-

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Delivery form

Natural Color

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa