

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	11500	MPa	ISO 527
Stress at break	195	MPa	ISO 527
Strain at break	3.5	%	ISO 527
Charpy impact strength, +23°C	90	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	80	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	17	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	12	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	23	kJ/m ²	ISO 180/1A
Izod notched impact strength	13	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	250	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	255	°C	ISO 75-1/-2
Vicat softening temperature, B	250	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Comparative tracking index	500	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1410	kg/m ³	ISO 1183
Moisture Content	0.2	%	-

Characteristics

Regional Availability

Europe