

Product Texts

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® 73G30HSL BK416 is a 30% glass fibre reinforced, heat stabilised polyamide 6 for injection molding.

| Processing/Physical Characteristics | dry / cond | Unit | Test Standard |
|--|------------|-------------------|-----------------|
| ISO Data | | | |
| ^[C] Molding shrinkage, parallel | 0.2 / * | % | ISO 294-4, 2577 |
| ^[C] Molding shrinkage, normal | 0.6 / * | % | ISO 294-4, 2577 |
| ^[C] Density of melt | 1200 | kg/m ³ | - |

[C]: CAMPUS

| Mechanical properties | dry / cond | Unit | Test Standard |
|--|-------------|-------------------|---------------|
| ISO Data | | | |
| ^[C] Tensile Modulus | 9500 / 6000 | MPa | ISO 527 |
| ^[C] Stress at break | 190 / 120 | MPa | ISO 527 |
| ^[C] Strain at break | 3.5 / 6 | % | ISO 527 |
| ^[C] Charpy impact strength, +23°C | 85 / 100 | kJ/m ² | ISO 179/1eU |
| ^[C] Charpy impact strength, -30°C | 80 / 80 | kJ/m ² | ISO 179/1eU |
| ^[C] Charpy notched impact strength, +23°C | 14 / 22 | kJ/m ² | ISO 179/1eA |
| ^[C] Charpy notched impact strength, -30°C | 10 / 11 | kJ/m ² | ISO 179/1eA |

[C]: CAMPUS

| Thermal properties | dry / cond | Unit | Test Standard |
|--|------------|--------|----------------------|
| ISO Data | | | |
| ^[C] Melting temperature, 10°C/min | 221 / * | °C | ISO 11357-1/-3 |
| ^[C] Glass transition temperature, 10°C/min | 60 / * | °C | ISO 11357-1/-2 |
| ^[C] Temp. of deflection under load, 1.80 MPa | 204 / * | °C | ISO 75-1/-2 |
| ^[C] Temp. of deflection under load, 0.45 MPa | 220 / * | °C | ISO 75-1/-2 |
| ^[C] Coeff. of linear therm. expansion, parallel | 12 / * | E-6/K | ISO 11359-1/-2 |
| ^[C] Coeff. of linear therm. expansion, normal | 100 / * | E-6/K | ISO 11359-1/-2 |
| ^[C] Burning Behav. at 1.5 mm nom. thickn. | HB / * | class | IEC 60695-11-10 |
| Thickness tested | 1.5 / * | mm | - |
| Yellow Card available | yes / * | - | - |
| ^[C] Burning Behav. at thickness h | HB / * | class | IEC 60695-11-10 |
| Thickness tested | 0.8 / * | mm | - |
| Yellow Card available | yes / * | - | - |
| ^[C] Burning rate, FMVSS, Thickness 1 mm | 30 | mm/min | ISO 3795 (FMVSS 302) |

[C]: CAMPUS

| Other properties | dry / cond | Unit | Test Standard |
|------------------------------------|------------|-------------------|----------------|
| ^[C] Water absorption | 6.3 / * | % | Sim. to ISO 62 |
| ^[C] Humidity absorption | 2.1 / * | % | Sim. to ISO 62 |
| ^[C] Density | 1360 / - | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Zytel® 73G30HSL BK416

PA6-GF30

Celanese

| Material specific properties | dry / cond | Unit | Test Standard |
|---------------------------------|------------|--------------------|---------------------|
| ISO Data | | | |
| ^[C] Viscosity number | 140 / * | cm ³ /g | ISO 307, 1157, 1628 |

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Black

Regional Availability

North America, Europe, Asia Pacific, South and Central America