

N5133G-BK1

PA6-GF33

Pontex Polyblend Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.2	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	113	MPa	ASTM D 638
Flexural Modulus	7357	MPa	ASTM D 790
Flexural Strength	177	MPa	ASTM D 790
Izod Impact notched, 1/8 in	108	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	200	°C	ASTM D 648

Characteristics**Regional Availability**

Asia Pacific