

PlusTek PB305G33BK43.2

PA6-GF33

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6	g/10min	ISO 1133
Temperature	235	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	10200	MPa	ISO 527
Strain at break	2.74	%	ISO 527
Flexural modulus, 23°C	9400	MPa	ISO 178
Flexural strength	263	MPa	ISO 178
Izod notched impact strength, +23°C	16.8	kJ/m ²	ISO 180/1A
Other Standards^[5]			
Tensile Strength	133	MPa	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Water absorption	6	%	Sim. to ISO 62
Humidity absorption	2	%	Sim. to ISO 62
Density	1380	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Mold temperature	65 - 80	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	240 - 280	°C	-
Zone 2	240 - 280	°C	-
Zone 3	240 - 280	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Black

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Chemical Resistance

Hydrolytically Stable

Certifications

Drinking water contact, Drinking water contact NSF 61, RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa