

Starflam RF0052E

(PA66+PA6)-GX

Eurostar Engineering Plastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	8100	MPa	ISO 527
Stress at break	120	MPa	ISO 527
Strain at break	2.7	%	ISO 527
Flexural modulus, 23°C	6700	MPa	ISO 178
Izod impact strength, +23°C	40	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	215	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	251	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	36	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	109	E-6/K	ISO 11359-1/-2
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.8	mm	-

Other properties	Value	Unit	Test Standard
Density	1370	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding, Other Extrusion

Features

Low Odor

Delivery form

Pellets

Regional Availability

Europe

Special Characteristics

Flame retardant