

**PlusTek PB304G7NT**

PA6-GF35

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	10800	MPa	ISO 527
Tensile Strength	195	MPa	ISO 527
Strain at break	4	%	ISO 527
Izod notched impact strength, +23°C	21	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	215	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Water absorption	5.5	%	Sim. to ISO 62
Humidity absorption	1.5	%	Sim. to ISO 62
Density	1400	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Mold temperature	65 - 80	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	240 - 280	°C	-
Zone 2	240 - 280	°C	-
Zone 3	240 - 280	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Natural Color

**Special Characteristics**

Heat stabilized or stable to heat

**Certifications**

Food contact, Food approval 10/2011, RoHS compliant

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa