

**4MID 9AB21130**

(PA66+PA6)-T30

4Plas

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	<b>1.2</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>0.9</b>	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>5000</b>	MPa	ISO 527
Stress at break	<b>90</b>	MPa	ISO 527
Strain at break	<b>10</b>	%	ISO 527
Izod notched impact strength, +23°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	<b>5</b>	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	<b>-30</b>	°C	-

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>262</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>130</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>225</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>240</b>	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8</b>	mm	-

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Volume resistivity	<b>1E13</b>	Ohm*m	IEC 62631-3-1
Surface resistivity	<b>1E13</b>	Ohm	IEC 62631-3-2
Comparative tracking index	<b>500</b>	-	IEC 60112

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1380</b>	kg/m <sup>3</sup>	ISO 1183
Moisture Content	<b>0.2</b>	%	-

**Characteristics****Regional Availability**

Europe