

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	11500 / 7300	MPa	ISO 527
^[C] Stress at break	195 / 130	MPa	ISO 527
^[C] Strain at break	3.2 / 0.6	%	ISO 527
Flexural modulus, 23°C	9000 / 7600	MPa	ISO 178
Flexural strength	315 / 205	MPa	ISO 178
^[C] Charpy impact strength, +23°C	95 / 100	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	15 / 25	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1420 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Black