

**AKROMID® B3 GF 40 1 black (20016)**

PA6-GF40

Akro-Plastic GmbH

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	<b>0.2 / *</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>0.6 / *</b>	%	ISO 294-4, 2577
<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>12500 / 8000</b>	MPa	ISO 527
Stress at break	<b>195 / 120</b>	MPa	ISO 527
Strain at break	<b>3 / 5</b>	%	ISO 527
Charpy impact strength, +23°C	<b>95 / 100</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>15 / 21</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>220 / *</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>210 / *</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>220 / *</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 8.00 MPa	<b>165 / *</b>	°C	ISO 75-1/-2
Burning behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-
<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Volume resistivity	<b>1E11 / 1E8</b>	Ohm*m	IEC 62631-3-1
Surface resistivity	<b>* / 1E10</b>	Ohm	IEC 62631-3-2
<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1460 / -</b>	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	<b>270</b>	°C	-
Mold temperature	<b>80</b>	°C	-
Injection pressure	<b>75</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Applications**

Automotive

**Delivery form**

Black

**Regional Availability**

Europe, Asia Pacific

**Special Characteristics**

Heat stabilized or stable to heat