

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	79.3	MPa	ASTM D 638
Elongation at Break	5	%	ASTM D 638
Flexural Modulus	6210	MPa	ASTM D 790
Izod Impact notched, 1/8 in	43	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	199	°C	ASTM D 648
Melting Temperature	260	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1550	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Additives

Lubricants

Regional Availability

North America