

NG40-01NC

PA6-GF40

Next Polymers Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0039	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0088	mm/mm	ASTM D 955
Mechanical properties	dry / cond	Unit	Test Standard
ASTM Data			
Tensile Strength	195 / 135	MPa	ASTM D 638
Elongation at Break	4 / 7	%	ASTM D 638
Flexural Modulus	11500 / 7500	MPa	ASTM D 790
Flexural Strength	260 / -	MPa	ASTM D 790
Rockwell Hardness	R 130 /	-	ASTM D 785
Izod Impact notched, 1/8 in	177 / 245	J/m	ASTM D 256
Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.8	mm	-
DTUL @ 66 psi	220	°C	ASTM D 648
DTUL @ 264 psi	210	°C	ASTM D 648
Melting Temperature	220	°C	ASTM D 3418
Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Volume resistivity	1E13 / 1E11	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E14	Ohm	IEC 62631-3-2
Electric strength	25 / 20	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	-	IEC 60112
Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	1.4	%	ASTM D 570
Water Absorption, Equilibrium	4.5	%	ASTM D 570
Density	1450	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Features

Thermal Stability

Delivery form

Natural Color

Regional Availability

Asia Pacific