Titalon 1450GFT

PA6-GF45 — Titan Plastics Compounds Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	**150**	MPa	ISO 527
Flexural modulus, 23°C	**10000**	MPa	ISO 178
Flexural strength	**230**	MPa	ISO 178
Charpy notched impact strength, +23°C	**20**	kJ/m²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	**190**	°C	ISO 75-1/-2
Burning behav. at thickness h	**HB**	class	IEC 60695-11-10

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	**1E11**	Ohm*m	IEC 62631-3-1
Surface resistivity	**1E14**	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	**1450**	kg/m³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	**80 - 100**	°C	-
Pre-drying - Time	**4**	h	-
Melt temperature	**230 - 260**	°C	-
Mold temperature	**60 - 100**	°C	-

Characteristics

Processing
Injection Molding

Delivery form
Natural Color

Regional Availability
Asia Pacific

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.