

Product Texts

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® 73G45L NC010 is a 45% glass fiber reinforced polyamide 6 resin for injection molding.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.1 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.001	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.01	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	14500 / 9700	MPa	ISO 527
^[C] Stress at break	230 / 160	MPa	ISO 527
^[C] Strain at break	3 / 5	%	ISO 527
^[C] Tensile creep modulus, 1h	* / 9400	MPa	ISO 899-1
^[C] Tensile creep modulus, 1000h	* / 7300	MPa	ISO 899-1
^[C] Charpy impact strength, +23°C	115 / 111	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	115 / 101	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	20 / 25	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	19 / 23	kJ/m ²	ISO 179/1eA

ASTM Data

Tensile Strength	214 / -	MPa	ASTM D 638
Elongation at Break	3 / -	%	ASTM D 638
Flexural Modulus	12070 / -	MPa	ASTM D 790
Izod Impact notched, 1/8 in	185 / -	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	55 / *	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	213 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	221 / *	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	215 / *	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	16 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	100 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
^[C] Burning rate, FMVSS, Thickness 1 mm	44	mm/min	ISO 3795 (FMVSS 302)
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	221	°C	ASTM D 648
DTUL @ 264 psi	213	°C	ASTM D 648

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	4.9 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.7 / *	%	Sim. to ISO 62
^[C] Density	1510 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Viscosity number	148 / *	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Features

Weldable

Delivery form

Pellets, Natural Color

Applications

General Purpose, Sports Equipment

Additives

Lubricants, Release agent

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa