

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.008	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	8300	MPa	ASTM D 638
Tensile Strength	145	MPa	ASTM D 638
Flexural Modulus	7200	MPa	ASTM D 790
Flexural Strength	210	MPa	ASTM D 790
Rockwell Hardness	R 115	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 66 psi	210	°C	ASTM D 648
DTUL @ 264 psi	200	°C	ASTM D 648
Melting Temperature	222	°C	ASTM D 3418

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dielectric Strength, Short Time	22	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.02	-	ASTM D 150
Dielectric Constant, 1 MHz	3.8	-	ASTM D 150
Volume Resistivity	1E15	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.9	%	ASTM D 570
Density	1310	kg/m³	ASTM D 792

Characteristics

Special Characteristics
High impact or impact modified

Regional Availability
North America, Asia Pacific

Applications
Automotive, Electrical and Electrical