

LATAMID 6 H2 G/20-V2HF

PA6-GF

LATI Industria Termoplastici S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	5500	MPa	ISO 527
Stress at break	80	MPa	ISO 527
Strain at break	3.5	%	ISO 527
Charpy impact strength, +23°C	30	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	175	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	190	°C	ISO 75-1/-2
Vicat softening temperature, B	205	°C	ISO 306
Coeff. of linear therm. expansion, parallel	75	E-6/K	ISO 11359-1/-2
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	2	mm	-
Glow Wire Ignition Temperature (GWIT)	725	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1	mm	-
Glow Wire Ignition Temperature (GWIT)	725	°C	IEC 60695-2-13
GWIT - thickness tested (2)	2	mm	-
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.75	mm	-
Limiting Oxygen Index	27	%	ASTM D 2863
Electrical properties			
ISO Data			
Comparative tracking index	550	-	IEC 60112
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257
Other properties			
Density	1320	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	230 - 250	°C	-
Mold temperature	70 - 100	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Special Characteristics

Flame retardant, Halogen-free, Phosphorus-free, Heat stabilized or stable to heat