

LATAMID 6 H2 G/55

PA6-GF

LATI Industria Termoplastici S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	17000	MPa	ISO 527
Stress at break	220	MPa	ISO 527
Strain at break	2.5	%	ISO 527
Charpy impact strength, +23°C	85	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	15	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	215	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	225	°C	ISO 75-1/-2
Vicat softening temperature, B	220	°C	ISO 306
Coeff. of linear therm. expansion, parallel	20	E-6/K	ISO 11359-1/-2

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1620	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	240 - 270	°C	-
Mold temperature	80 - 100	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Special Characteristics

Heat stabilized or stable to heat