

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	10500	MPa	ISO 527
Stress at break	105	MPa	ISO 527
Strain at break	2.3	%	ISO 527
Charpy impact strength, +23°C	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	195	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	215	°C	ISO 75-1/-2
Vicat softening temperature, B	210	°C	ISO 306
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.75	mm	-
Electrical properties			
ASTM Data			
Surface Resistivity	1E8	Ohm	ASTM D 257
Other properties			
Density	1340	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	230 - 250	°C	-
Mold temperature	70 - 100	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Special Characteristics

Increased electrical conductivity, Flame retardant, Halogen-free, Phosphorus-free