

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	6300	MPa	ISO 527
Yield stress	84	MPa	ISO 527
Yield strain	2.3	%	ISO 527
Stress at break	81	MPa	ISO 527
Flexural modulus, 23°C	5500	MPa	ISO 178
Izod impact strength, +23°C	35	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	158	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	206	°C	ISO 75-1/-2
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.75	mm	-

Other properties	Value	Unit	Test Standard
Water absorption	1.9	%	Sim. to ISO 62
Density	1370	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Special Characteristics

Flame retardant

Features

Low Odor

Regional Availability

Europe