

Starflam PX06011

PA6-GF

Eurostar Engineering Plastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	93	MPa	ISO 527
Strain at break	2.1	%	ISO 527
Flexural modulus, 23°C	6300	MPa	ISO 178
Izod impact strength, +23°C	30	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	3	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	196	°C	ISO 75-1/-2
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	1.6	mm	-

Other properties	Value	Unit	Test Standard
Density	1430	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Pellets

Special Characteristics

Flame retardant

Features

Low Odor

Regional Availability

Europe