

LUVOCOM 1-3260

(PA66+PTFE)

LEHVOSS Group

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.4	%	ISO 294-4, 2577
Thermal conductivity of melt	0.23	W/(m K)	-
Mechanical properties			
ISO Data			
Tensile Modulus	2500	MPa	ISO 527
Tensile Strength	65	MPa	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Charpy impact strength, -30°C	80	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Vicat softening temperature, A	230	°C	ISO 306
Coeff. of linear therm. expansion, parallel	60	E-6/K	ISO 11359-1/-2
Electrical properties			
ISO Data			
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Other properties			
Density	1250	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	75	°C	-
Pre-drying - Time	6 - 16	h	-
Processing humidity	≤0.1	%	-
Melt temperature	290	°C	-
Mold temperature	90 - 120	°C	-
Zone 1	290 - 310	°C	-
Zone 2	290 - 310	°C	-
Zone 3	290 - 310	°C	-
Nozzle temperature	280 - 300	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Black

Additives

Lubricants

Special Characteristics

Heat stabilized or stable to heat

Features

Tribologic Grade

Applications

Automotive, IT / Business Machine

Regional Availability

North America, Europe, Asia Pacific