

AKROMID® B28 GF 50 1 GIT black (5649)

PA6-GF50

Akro-Plastic GmbH

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	16700 / 10500	MPa	ISO 527
Stress at break	235 / 150	MPa	ISO 527
Strain at break	3 / 4.5	%	ISO 527
Charpy impact strength, +23°C	105 / 105	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	20 / 25	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

Other properties	dry / cond	Unit	Test Standard
Density	1550 / -	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	270	°C	-
Mold temperature	80	°C	-
Injection pressure	75	MPa	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Black

Regional Availability

Europe, Asia Pacific