

Product Texts

50% Glass Reinforced, Heat Stabilized, High Flow

ISO 1043 PA6-GF50

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	15 / *	cm ³ /10min	ISO 1133
Temperature	275 / *	°C	-
Load	2.16 / *	kg	-
^[C] Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577
^[C] Density of melt	1360	kg/m ³	-
^[C] Thermal conductivity of melt	0.3	W/(m K)	-
^[C] Spec. heat capacity of melt	1870	J/(kg K)	-
^[C] Eff. thermal diffusivity	1.18E-7	m ² /s	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	16500 / 11000	MPa	ISO 527
^[C] Stress at break	235 / 155	MPa	ISO 527
^[C] Strain at break	2.7 / 5	%	ISO 527
^[C] Charpy impact strength, +23°C	90 / 100	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	85 / 85	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	15 / 25	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	12 / 12	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	210 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	220 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	30 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	40 / *	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	5.5 / 12	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	4.5 / 4.9	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	360 / 3250	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	270 / 770	E-4	IEC 62631-2-1
^[C] Comparative tracking index	500 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	4.5 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.4 / *	%	Sim. to ISO 62
^[C] Density	1560 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Akulon® Ultraflow K-FHG0

PA6-GF50

Envalior

Processing

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific

Other text information

Injection molding

[Injection Molding Recommendations](#)