

DANAMID FGF- 50

PA6-GF50

Qualchem Zrt.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	150	MPa	ISO 527
Strain at break	4	%	ISO 527

Electrical properties	Value	Unit	Test Standard
ISO Data			
Comparative tracking index	550	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1510	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Europe