

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>16300 / 10000</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>185 / 115</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>1.8 / 5.5</b>	%	ISO 527
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>12 / 17.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>213 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>218 / *</b>	°C	ISO 75-1/-2

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>- / 1560</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Delivery form**  
Black

**Certifications**  
Recycled Resin Content