

Product Texts

50% Glass Reinforced, Injection Molding

ISO 1043 PA6-GF50

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	2 / *	cm ³ /10min	ISO 1133
Temperature	250 / *	°C	-
Load	2.16 / *	kg	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	15000 / -	MPa	ISO 527
^[C] Stress at break	230 / -	MPa	ISO 527
^[C] Strain at break	4.1 / -	%	ISO 527
^[C] Charpy impact strength, +23°C	105 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	20 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Humidity absorption	1.4 / *	%	Sim. to ISO 62
^[C] Density	1570 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific

Delivery form

Pellets, Black, Natural Color

Other text information**Injection molding**[Injection Molding Recommendations](#)[Steel recommendations for molds screws and barrels](#)[Trouble shooting guideline for injection molding](#)