

PlusTek PB202G50BK39F

PA6-GF50

Polyram

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	15500	MPa	ISO 527
Tensile Strength	205	MPa	ISO 527
Strain at break	2.8	%	ISO 527
Izod notched impact strength, +23°C	20	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	215	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1550	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.15	%	-
Mold temperature	90 - 95	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	290 - 300	°C	-
Zone 2	290 - 300	°C	-
Zone 3	290 - 300	°C	-

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Delivery form

Black

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat