

Product Texts

Polyamide 6, 50% glass fiber reinforced, improved flowability, for injection moulding, natural color

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	16500 / 10500	MPa	ISO 527
^[C] Stress at break	230 / 140	MPa	ISO 527
^[C] Strain at break	3 / 6	%	ISO 527
Flexural modulus, 23°C	15000 / 9000	MPa	ISO 178
Flexural strength	350 / 230	MPa	ISO 178
^[C] Charpy impact strength, +23°C	100 / 120	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	90 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	20 / 25	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	15 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	210 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	220 / *	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	215 / *	°C	ISO 306
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E14	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1560 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Applications

Automotive

Delivery form

Natural Color