

Product Texts

LNP THERMOCOMP PF00C compound is based on Nylon 6 resin containing 60% glass fiber.

UL Yellow Card Link [E207780-103093414](https://www.ulprospector.com/PA66/properties/207780-103093414)

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	22380	MPa	ASTM D 638
Tensile Strength at Break	210	MPa	ASTM D 638
Elongation at Break	2.4	%	ASTM D 638
Flexural Modulus	19380	MPa	ASTM D 790
Flexural Strength	365	MPa	ASTM D 790
Izod Impact notched, 1/8 in	170	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	1230	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
ASTM Data			
DTUL @ 264 psi	210	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1710	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific