

Product Texts

60% Continuous Glass Fiber Reinforced, Uni-Directional Tape, Heat Stabilized, Black

ISO 1043 PA6-GF60

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	60 / *	°C	ISO 11357-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Humidity absorption	1 / *	%	Sim. to ISO 62
^[C] Density	1700 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Thermoforming

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Tape, Black

Regional Availability

North America, Europe, Asia Pacific