

Product Texts

Injection Molding, 20% Glass Beads Reinforced, Flame Retardant (halogen free), Heat Stabilized

ISO 1043 PA6-GX20 FR(40+30)

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.6 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	5100 / 2100	MPa	ISO 527
^[C] Stress at break	80 / 42	MPa	ISO 527
^[C] Strain at break	3.5 / 30	%	ISO 527
Flexural modulus, 23°C	5000 / 2000	MPa	ISO 178
Flexural strength	140 / 60	MPa	ISO 178
^[C] Charpy impact strength, +23°C	30 / 105	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	- / 10	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	25 / 85	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	10 / 10	kJ/m ²	ISO 180/1A

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	160 / *	°C	ISO 75-1/-2
Vicat softening temperature, B	205 / *	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	50 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	80 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Burning behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	0.75	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	1.5	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (3)	3	mm	-
Glow Wire Ignition Temperature (GWIT)	700	°C	IEC 60695-2-13
GWIT - thickness tested (1)	0.75	mm	-
Glow Wire Ignition Temperature (GWIT)	700	°C	IEC 60695-2-13
GWIT - thickness tested (2)	1.5	mm	-
Glow Wire Ignition Temperature (GWIT)	700	°C	IEC 60695-2-13
GWIT - thickness tested (3)	3	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Comparative tracking index	525 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	7.3 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2.2 / *	%	Sim. to ISO 62
^[C] Density	1290 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Durethan® BKV20FN27 000000

PA6-GX20 FR(40+30)

Envalior

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	260	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.07	%	-
Melt temperature	250 - 270	°C	-
Mold temperature	80 - 100	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant, Halogen-free, Heat stabilized or stable to heat

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

PREPROCESSING

Residual moisture content: 0.03 - 0.07%

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

PROCESSING

Melt temperature (Tmin - Tmax): 250 - 270 °C

Mold temperature: 80 - 100 °C