

**Product Texts**

Polyamide 6, low temperature impact modified, for injection moulding, natural color

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	165 / *	cm <sup>3</sup> /10min	ISO 1133
Load	5 / *	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	1.7 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.5 / *	%	ISO 294-4, 2577

[C]: CAMPUS

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2700 / -	MPa	ISO 527
Flexural modulus, 23°C	2200 / -	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	10 / -	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	1100 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified

**Delivery form**

Natural Color