

**Product Texts**

Base Polymer	Polyamide 6
Filler/Additive System	15 % glass fibres,UV stabilised
Market Segment	Automotive,building and construction,various
Application Area	cooling system,fuel systems,gear wheels, roller bearings,various
Typical Applications	oil pump parts,bearings and sliding elements,engine cover,various

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>5300 / -</b>	MPa	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>65 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>10 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>201 / *</b>	°C	ISO 75-1/-2

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1220 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific, Near East/Africa

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather

**Other text information****Injection molding**

Pre-Drying Conditions      80 °C in a dry air (dessiccant) dryer  
for 2-12 h  
dependant on moisture content  
max. moisture content <0,15 %

Processing Injection Moulding      melt temperature 270-290 °C  
mould temperature 80-100 °C

Storage      dry, protected from light  
not above 30°C